

POLYESTER MONOFILAMENT

Technische Richtwerte / Erhältlichkeit

[info@waengi-mesh.ch](mailto:info@waengi-mesh.ch)

Gewebe- bezeichnung	Maschen- weite	Offene Fläche	Faden- zahl	Faden- d'messer	Gewebe- dicke	Gewicht
	my	%	cm	my	my	g/m2
375 / 46	375	46	18	180	330	128
295 / 50	295	50	24	120	215	81
250 / 45	250	45	27	120	210	91
245 / 60	245	60	32	70	107	36
200 / 46	200	46	32	100	158	74
150 / 54	150	54	48	55	90	34
145 / 42	145	42	43	80	125	62
130 / 42	130	42	48	70	108	60
115 / 41	115	41	54	64	98	52
105 / 52	105	52	68	40	60	28
95 / 35	95	35	61	64	102	59
82 / 36	82	36	68	55	84	50
76 / 38	76	38	77	48	76	42
70 / 31	70	31	77	55	85	55
68 / 38	68	38	90	40	60	37
58 / 35	58	35	100	40	61	37
55 / 27	55	29	90	48	78	50
54 / 38	54	38	110	34	51	32
51 / 18	51	18	83	60	110	72
49 / 38	49	38	120	31	48	27
43 / 32	43	32	120	34	53	35
41 / 14	41	14	90	64	125	83
36 / 22	36	22	120	40	63	44
32 / 24	32	24	150	31	44	32
30 / 22	30	22	140	34	52	40
25 / 18	25	18	150	34	52	32
21 / 16	21	16	165	31	46	36
20 / 18	20	18	180	27	43	31

Lieferbar in Breiten und Farben

	108/115	132/137	154/157	204/208	230/234	306/310 cm
375 / 46	n.a.	n.a.	W	n.a.	n.a.	n.a.
295 / 50	W	n.a.	n.a.	W	W	n.a.
250 / 45	W	W	n.a.	W	n.a.	n.a.
245 / 60	W	W	W	W	W	W
200 / 46	W	W	W	W	W	W
150 / 54	W	W	W	W	W	W
145 / 42	W	W	W	W	W	W
130 / 42	W	W	W	W	W	W
115 / 41	W	W	W	W	W	W
105 / 52	W	n.a.	n.a.	W	W	n.a.
95 / 35	W	W	W	W	W	W
82 / 36	W	W	W	W	W	W
76 / 38	W	W	W	W	W	W
70 / 31	W	W	W	W	W	W
68 / 38	W	W	W	W	W	W
58 / 35	W	W	W	W	W	W
55 / 27	W	W	W	W	W	W
54 / 38	W	W	W	W	W	W
51 / 18	W	n.a.	n.a.	W	W	n.a.
49 / 38	W	W	W	W	W	W
43 / 32	W	W	W	W	W	W
41 / 14	W	n.a.	n.a.	W	W	n.a.
36 / 22	W	W	W	W	W	W
32 / 24	W	W	W	W	W	W (eff. 280)
30 / 22	W	W	W	W	W	W (eff. 280)
25 / 18	W	W	W	W	W	W (eff. 280)
21 / 16	W	n.a.	W	W	W	n.a.
20 / 18	W	n.a.	W	n.a.	n.a.	n.a.

Standard Farben: Weiss, Spezialfarben ab 500 lfm/Farbe möglich

Standard Längen/Breiten: ca. 25, 50, 100 oder 200 lfm, Spezialbreiten ab 200 lfm

Spezifikationen sind nominale Werte, Fabrikationsänderungen vorbehalten, 09.03.09 / cle